

▸ Application

PVC Calenderings Leathers, Sheets,Gloves,Hose

▸ Feature

LGflex GL300 / DI OCTYL TEREPHTHALATE Excellent Viscosity and Heat Stability Non-endocrine distrupter

▸ Properties

-	Method	Condition	Unit	Value
Color	JIS K6751	-	APHA	MAX. 20
Acidity	JIS K6751	-	KOH mg/g	MAX. 0.02
Acid Value After Heating	JIS K6751	after125°Cx3hr	KOH mg/g	MAX. 0.07
Ester Value	JIS K6751	-	-	287 ± 3
Refractive Index	JIS K6751	25°C	nD20	1.487 ± 0.003
Heat Loss	JIS K6751	125°Cx3hr	wt.%	MAX. 0.07
Molecular Weight		-	-	390.56
Freezing Point		-	°C	-48
Flash Point		-	°C	238
Boiling Point		@760mmHg	°C	400
Viscosity		20°C	cps	82